

LL7903A

Metallocene Linear Low Density Polyethylene Resin

Special Characteristics : InnoPlus LL7903A resin is a metallocene polyethylene with hexene comonomers, without slip and antiblock. This grade is an easy processing grade which offers an outstanding balance between processing and film properties. Films extruded from InnoPlus LL7903A have high tensile, Impact strength and puncture properties.

Typical Applications : InnoPlus LL7903A is recommended for producing the heavy duty films, lamination films, shrink film, stand-up pouches, multi-layer packaging films and freezer packaging films.

Typical Properties :

Properties	LL7903A	Unit	Test Method
<i>Physical Properties</i>			
Melt Index (190 °C, 2.16 kg)	0.3	g/10 min	ASTM D1238
Density	0.927	g/cm ³	ASTM D792
Melting Point	122	°C	ASTM D3418
Vicat Softening Point	114	°C	ASTM D1525
<i>Film Properties*</i>			
Tensile Strength at Break (MD/TD)	40 / 44	MPa	ASTM D882
Elongation at Break (MD/TD)	500 / 700	%	ASTM D882
Tensile Modulus, 1% Secant (MD/TD)	310 / 370	MPa	ASTM D882
Dart Impact Strength	140	g	ASTM D1709
Tear Strength (MD/TD)	90 / 600	g	ASTM D1922
Haze	20	%	ASTM D1003
Gloss (45°)	55	-	ASTM D2457

* Film made on blown film line at blow up ratio 2.5. Gloss (45°) obtained from 40 microns film while other film properties obtained from 25 microns film.

Processing Condition :

The recommended temperature setting is in the range of 160 - 180 °C for extruder and 170 - 190 °C for die zone.

FDA Statement :

mLLDPE under the brand InnoPlus complies with U.S. FDA 21 CFR 177.1520 (c) (2.1) and (2.2) regulation for polyethylene used in articles that contact food suitable for articles used for packaging or holding food during cooking.

Disclaimer :

This Applications specified herein is for reference only and not suitable for using in the manufacturing of any products in medical and pharmaceutical sectors.

- Determination of suitability of the product for the use and purpose shall be the customer's responsibility. Customer is obligated to inspect and test the product for such suitability. Customer is responsible for appropriate, safe, legal use processing and handling of the product.
- To our best knowledge, information contained herein is true and accurate as of the date of its publication. However, we make no representations or warranties with respect to accuracy, reliability and completeness of the information contained herein for any purpose.
- No warranties, express or implied, which extend beyond the description herein are given by us. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- We assume no liability for any use of the product in combination with other materials. The information contained herein entirely relates to the product when it is not used in combination with any third party's materials.

Note : Properties reported here are typical values of the product, not to be considered as specifications.

PTT Global Chemical makes no representations as to the accuracy or completeness of the information contained herein.