

LL9630U2 / LL9630U2P

Linear Low Density Polyethylene Resin

Special Characteristics : LL9630U2 and LL9630U2P are hexene comonomer based linear low density polyethylene designed for rotational molding applications. This grade is UV20 resistance level pelletized rotational molding resin with high stiffness and an excellent balance of processability and environmental stress cracking resistance.

InnoPlus LL9630U2P is a powder form of InnoPlus LL9630U2

Typical Applications : InnoPlus LL9630U2 and LL9630U2P can be used to produce variety applications such as general molding, toys & playground equipment, storage containers, medium to large water tanks and chemical tanks.

Typical Properties :

Properties	LL9630U2 /LL9630U2P	Unit	Test Method
<i>Physical Properties</i>			
Melt Flow Rate (190 °C, 2.16 kg)	3.2	g/10 min	ASTM D1238
Density	0.938	g/cm ³	ASTM D792
Brittleness Temperature	< -70	°C	ASTM D3418
Vicat Softening Point	118	°C	ASTM D1525
Heat Distortion Temperature @ 0.455 MPa	60	°C	ASTM D648
<i>Mechanical Properties (Compression specimens)*</i>			
Tensile Strength at Yield	20	MPa	ASTM D638
Tensile Strength at Break	30	MPa	ASTM D638
Elongation @ Break	1000	%	ASTM D638
Flexural modulus	750	MPa	ASTM D790
Durometer Hardness	60	Shore D	ASTM D2240
ESCR, F ₅₀ (Condition A 100% Igepal)	> 1000	Hours	ASTM D1693
Arm Impact Strength @ -40°C (3 mm Rotomolded sample)	65	J	ARM Method

Processing Condition :

The recommended oven temperature is in the range of 260 - 290 °C.

FDA Statement :

LLDPE under the brand InnoPlus complies with U.S. FDA 21 CFR 177.1520 (c) (2.1) and (2.2) regulation for polyethylene used in articles that contact food suitable for articles used for packaging or holding food during cooking.

Disclaimer :

This Applications specified herein is for reference only and not suitable for using in the manufacturing of any products in medical and pharmaceutical sectors.

- Determination of suitability of the product for the use and purpose shall be the customer's responsibility. Customer is obligated to inspect and test the product for such suitability. Customer is responsible for appropriate, safe, legal use processing and handling of the product.
- To our best knowledge, information contained herein is true and accurate as of the date of its publication. However, we make no representations or warranties with respect to accuracy, reliability and completeness of the information contained herein for any purpose.
- No warranties, express or implied, which extend beyond the description herein are given by us. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- We assume no liability for any use of the product in combination with other materials. The information contained herein entirely relates to the product when it is not used in combination with any third party's materials.

Note : Properties reported here are typical values of the product, not to be considered as specifications.

PTT Global Chemical makes no representations as to the accuracy or completeness of the information contained herein.